

Zinc-200™

DESCRIPTION

This 95% pure zinc formula offers the ultimate corrosion protection for ferrous metals even if the surface gets scratched. It meets ASTM A-780 for industry compliance. The dull gray finish makes it the zinc coating of choice for the touch-up of aged hot dipped parts and can be used as a very effective primer for equipment exposed to weather or harsh environments.

- 95% pure zinc, fights off rust & corrosion
- Double action protection: resin coat and galvanic action
- Long-term protection even in harsh environments
- Dull grey finish
- Special low VOC formula
- Meets ASTM A780

APPLICATIONS

Manufacturing, repair and installation of:

- Fencing
- Outside structures
- Playground and sports equipment
- Scaffolding
- Water and storage tanks
- Ducting and air conditioning systems
- Pipe work
- Food processing equipment
- Roofing
- Siding
- Electric junction boxes
- Metal cabinets
- Outside plant and machinery
- Marine Equipment
- Architectural and ornamental structures
- Fasteners,
- Anchors, etc.

SURFACE PREPARATION

Remove any loose dirt, rust, mil scale and paint residues.

Clean, degrease and dry surface. For optimal results sand blast surface to be treated.

TECHNICAL DATA

Physical state: Aerosol

Colour: Aluminium

Density: 1.49 to 1.53g/ml (20°C / 68°F)

VOC: 55% (w/w)

Flash Point: 4°C / 39.2°F

Zinc content in dry film: >92%

Working temperatures: softens at 66°C (150°F)

Withstands up to 2000 hours 5% salt spray

Coverage: 25 to 28 sq.ft. @ 3 mil thickness

Drying: to touch in 3 to 5 min., hard in 48 hrs. (1 mil, 25°C)

Engineering controls: ensure proper ventilation, remove all ignition sources

Incompatible substances: strong oxidizers

Storage: store in a well ventilated area, below 50°C/120°F

Shelf life: 2 years in closed container, stored in ideal conditions

APPROVALS

- Meets ASTM A 780-93 and ASTM A 780-01,
- CFIA approved for use in food plants

ORDERING INFORMATION

Description	Size	Order No.	(M)SDS
Aerosol	326g	53-H 152	L-95E

(M) SDS available upon request or visit our web site at www.walter.com

Not for product specification. The technical data contained herein is intended as reference only and may change without notice.